




TECHNICAL DATA SHEET

HANDI-SEAL® WINDOW & DOOR FOAM SEALANT

LOW PRESSURE POLYURETHANE FOAM SEALANT INFORMATION

Description	Low pressure and low pressure building, one-component, polyurethane foam sealant
OCF	One Component Foam
Applications	Designed to seal rough opening around doors and windows.
Preparation for use	Substrate must be clean, dry, free of loose particles, and free of dust, grease and mold release agents.
Use	Optimal product temperature is 65-80°F (18-27°C). Gun foam option: attach the container to the dispensing unit (Handi-Tool), shake well, and begin dispensing. The dispensing units can be metered by pulling the dispensing unit trigger for the desired rate, or with the metering screw located in the back. Foam application can be interrupted when needed as outlined in the instructions and the dispensing unit will be ready for immediate re-use, as long as it remains attached to a pressurized container. An empty gun foam container must be replaced with a new container. Straw foam option: attach the straw, shake well, invert the container, and begin dispensing. By activating the adapter lever carefully, the extrusion rate can be regulated.
PPE	 <p>Use only in a well-ventilated area. Wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Read all instructions and safety information prior to use. Consult the product's SDS (available at www.fomo.com).</p>
Note	FOR PROFESSIONAL USE ONLY. Always check the local building code before use. Cured low pressure polyurethane foam is non-toxic and inert.
Product Storage	Store upright in a dry area. Do not expose the product to open flame or temperatures above 122°F (50°C). Storage in excessive heat can cause premature aging of components resulting in a shorter shelf-life.
Temperature	For best results, chemical temperature must be between 65-80°F (18-27°C). Cured foam is resistant to heat and cold, -200°F to 240°F (-129°C to 116°C).
Disposal	Refer to SDS (Section 13) for instructions. Do not incinerate containers. Relieve containers of any remaining pressure and foam before discarding. Always wear PPE during the disposal process and make sure discarded foam is fully cured.
Shelf-life	12 months (expiration date located on the bottom of the container).
Compatibility	Cured low pressure polyurethane foam is chemically inert and non-reactive in approved applications, and will not harm electrical wire insulations, Romex®, rubber, PVC, polyethylene (i.e. PEX) or other plastics. The product is not resistant to UV rays, if left exposed the product should be coated or painted.

TECHNICAL DATA	STANDARD	RESULTS
Density-Gun foam	ASTM D1622	1.44 lbs/ft ³ (23 kg/m ³)
Density-Straw foam		1.60-1.90 lbs/ft ³ (25.6-30.4 kg/m ³)
K-factor	ASTM C518	0.194 BTU·inch/ft ² ·h·°F
R-Value	ASTM C518	5.16 per Inch
Air Barrier Properties (estimated)		
@1.57 psf (75 Pa)	ASTM E283	<0.0025 cfm/ft2 (<0.0125 L/s/m2)
Compressive Strength <i>Parallel to rise</i>	ASTM D1621	3.62 psi (14.9 kPa)
Durability	CAN/ULC 710.1	Passes
Dimensional Stability	ASTM D2126	+/- 5%
Tack-Free	Tack-Free	Approx. 5 minutes
Closed-Cell Content	ASTM D2856	68%

Cuttable		1 hour
Pressure Build	AAMA 812	1.89 psig
Fire Rating- Caulking & Sealant Tested 2 beads @ 3/4" Thickness	ASTM E84/UL 723	Flame Spread Index 5 Smoke Developed 10

APPROVALS/STANDARDS/CLASSIFICATIONS

ASTM E84/UL 723	UL Classified File #R13919	GREENGUARD- Gold Certification
NFPA 30B	Level 1 Aerosol	ASTM E2112- section 5.9.2
VOC Content (calculated minus exempt compounds)	0 g/L or 0%	CSA A440.4-98
AAMA 812	Compliant	



TEMPERATURE

Product Storage	<122°F (50°C)
Application (Substrate)	40-100°F (5-38°C)
Chemical	65-80°F (18-27°C)

YIELD¹ Linear Feet (Meters)

	¼" (6.3 mm)	3/8" (9.5mm)	½" (12.7mm)	Volume
12oz (340g) P40030 (Straw foam)	1379 ft (420 m)	613 ft (187 m)	345 ft (105 m)	.47 ft ³ (14.7 L)
24oz (680g) P10141 (Straw foam)	2140 ft (652 m)	950 ft (290 m)	534 ft (163 m)	.79 ft ³ (22.4 L)
24oz (680g) P10131 (Gun foam)	2900 ft (420 m)	1290 ft (393 m)	726 ft (221 m)	1.04 ft ³ (29.5 L)

¹ Yield is based on density. We state our core density when describing the foam. We use theoretical calculations for comparative purposes so the results will vary depending on ambient conditions and use in particular applications.

Always read all operating, application and safety instructions before using any products. Use in conformance with all local, state and federal regulations and safety requirements. Failure to strictly adhere to any recommended procedures and reasonable safety precautions shall release Fomo Products, Inc. of all liability with respect to the materials or the use thereof. For additional information and location of your nearest distributor, call Fomo Products, Inc. 1 330.753.4585 or 1 800.321.5585.

NOTE: Physical properties shown are typical and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions and may vary upon use, temperature and ambient conditions. Right to change physical properties as a result of technical progress is reserved. This information supersedes all previously published data. The Customer is responsible for deciding whether products and associated TDS information are appropriate for customer's use.

Handi-brand® low pressure one-component polyurethane foam sealants and adhesives (OCF), low pressure spray polyurethane foams (SPF), and low pressure pour-in-place polyurethane foams (PIP) are composed of a diisocyanate, hydrofluorocarbon or hydrocarbon blowing agent, and polyol. For polyurethane foam sealants/adhesives: wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Use only in a well-ventilated area. Avoid breathing vapors. Read the (M)SDS and instructions carefully before use (www.fomo.com). For spray polyurethane foams and pour-in-place polyurethane foams: wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Use only in a well-ventilated area and with certified respiratory protection or a powered air purifying respirator (PAPR). Additional information on ventilation can be found in the Product Stewardship Guide (www.fomo.com). Read the (M)SDS (www.fomo.com) and instructions carefully before use. The urethane foam produced from these ingredients will support combustion and may present a fire hazard if exposed to a fire or excessive heat about 240°F (116°C). Refer to each product's TDS for specifications, testing results, and other attributes. The customer is ultimately responsible for deciding whether products and associated TDS information are appropriate for customer's use. Refer to the products' (M)SDS, Fomo's Product Stewardship Guidelines, and operating instructions for guidance on the safe and proper application of the product (www.fomo.com). For professional use only. Building practices unrelated to materials can lead to potential mold issues. Material suppliers cannot provide assurance that mold will not develop in any specific system.

WARNINGS: Follow safety precautions and wear protective equipment as recommended. Prolonged inhalation exposure may cause respiratory irritation/sensitization and/or reduce pulmonary function in susceptible individuals. Onset may be delayed. Pre-existing respiratory conditions may be aggravated. Use only in a well-ventilated area and with certified respiratory protection. NIOSH approved positive pressure supplied air respirator is recommended if exposure guidelines may be exceeded. Contents may be very sticky and irritating to skin and eyes, therefore wear safety glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure when operating. If liquid chemical comes in contact with skin, first wipe thoroughly with dry cloth, then rinse affected area with water. Wash with soap and water afterwards, and apply hand lotion if desired. If liquid comes in contact with eyes, immediately flush with large volume of clean water for at least 15 minutes and get medical help at once. If liquid is swallowed, get immediate medical attention. Do not induce vomiting. If breathing is difficult, give oxygen. If breathing has stopped give artificial respiration. Products manufactured or produced from these chemicals are organic and, therefore, combustible. Each user of any product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage. **KEEP OUT OF REACH OF CHILDREN.**

LIMITED WARRANTY: The Manufacturer warrants only that the product shall meet its specifications: THIS WARRANTY IS IN LIEU OF ALL WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES AND THE MANUFACTURER EXPRESSLY DISCLAIMS ANY WARRANTY OF MERCHANTABILITY, OR FITNESS FOR A PARTICULAR PURPOSE. The buyer assumes all risks whatsoever as to the use of the material. Buyer's exclusive remedy as to any breach of warranty, negligence or other claim shall be limited to the replacement of the material. Failure to strictly adhere to any recommended procedures shall release The Manufacturer of all liability with respect to the materials or the use thereof. User of this product must determine suitability for any particular purpose, including, but not limited to, structural requirements, performance specifications and application requirements prior to installation and after product is applied.

Fomo Products, Inc.
A Member of the FLM Group of Companies
management system registered to ISO 9001



2775 Barber Road Norton, Ohio 44203 USA
1.330.753.4585 1.800.321.5585 Fax: 1.330.753.5199