



DURAL FAST SET LV

LOW VISCOSITY, RAPID SETTING, HIGH MODULUS EPOXY ADHESIVE

DESCRIPTION

DURAL FAST SET LV is a two-component, 100% solids, moisture insensitive, rapid-setting epoxy adhesive and binder for numerous applications. This high modulus, low viscosity epoxy resin is the perfect solution for general bonding applications and for injecting cracks in concrete and a variety of other substrates. DURAL FAST SET LV can be used in temperatures as low as 35°F (2°C) and rising.

PRIMARY APPLICATIONS

- Bonding of concrete, masonry or wood
- Injection resin for cracked, structural substrates
- Gravity feed cracks in concrete slabs
- Mix with dried silica sand to create a repair mortar

FEATURES/BENEFITS

- Exceptional adhesion to construction materials
- Low viscosity penetrates deep into cracks
- Easy to use 1:1 mix ratio
- Moisture insensitive
- Impeccable bond strength

TECHNICAL INFORMATION

The following information was obtained under laboratory conditions.

PROPERTY	RESULT
Mixed Viscosity, cp	500
Gel Time, minutes ASTM C 881	6 to 8
Compressive Strength, psi (MPa) ASTM D 695	7 days: 10,942 (75)
Compressive Modulus, psi (MPa) ASTM C 695	7 days: 3.78×10^5 (2,606)
Bond Strength, psi (MPa) ASTM C 882	14 days: 2,267 (16)
Water Absorption @ 24 hours, % ASTM D 570	0.4
Appearance/Color	Amber

PACKAGING

DURAL FAST SET LV is packaged in 4 gal (15 L) and 10 gal (38 L) units and cases of 12/22 oz. (650 ml) and 24/10 oz. (300 ml) cartridges. The mix ratio is 1:1 by volume.

SHELF LIFE

2 years in original, unopened containers

SPECIFICATIONS/COMPLIANCES

Complies with ASTM C 881-10 Types I and IV, Grade 1, Class A, B and C
Canadian MTQ

COVERAGE/YIELD

For injection, one neat gal (3.8 L) yields 231 in³ (.004 m³) of epoxy. One gal (3.8 L) of neat DURAL FAST SET LV epoxy mixed with 3 gal (11.4 L) of dry 20/40 mesh silica sand will yield approximately 643 in³ (.011m³) of mortar.

DIRECTIONS FOR USE

Surface Preparation: Concrete: The surface must be structurally sound, dry, free of grease, oils, coatings, dust, curing compounds and other contaminants. Surface laitance must be removed. The preferred method of surface preparation is abrasive blasting or other mechanical means per ICRI Guideline 310.2. Oil contaminated surfaces should be degreased. Remove defective concrete down to sound material. Route cracks and blow dust and debris from them with oil-free, compressed air. Following surface preparation, the cleaned surface should pull concrete when tested with a pull tester, or an elcometer (ASTM D 4541). **Steel:** All oils, grease, dirt, old coatings and chemical contaminants must be removed. The surface should be blasted to a near white metal finish (SSPC SP10) using clean, dry aggregate.

Mixing: Premix Part A and B with a slow speed motor and “Jiffy” mixer. Pour one part by volume of Part A and one part by volume of Part B into a clean, dry container and mechanically mix slowly for 3 minutes. Scrape the sides and bottom of mixing container while mixing. Do not whip or aerate while mixing. **Mortar:** Gradually add clean, dry 20/40 mesh silica sand to mixed epoxy. Blend thoroughly. The mix ratio of aggregate to binder is approximately 3:1 by volume, but may vary depending upon the desired consistency of the mortar.

Application: Application and surface temperatures should be at least 35°F (2°C) and rising. **Anchoring bolts, dowels, pins:** DURAL FAST SET LV can be used neat or with an aggregate to anchor horizontal bolts. The anchor bolt hole should be free of all debris before grouting. The optimum hole size is 1/8” (3.2 mm) annular space or 1/4” (6.4 mm) larger diameter than bar diameter. Depth of embedment is typically 10 to 15 times bolt diameter. **Vertical and overhead repairs:** Mix DURAL FAST SET LV into a mortar as described above. Apply neat DURAL FAST SET LV as a prime coat to the prepared concrete surface and apply the mortar to the area by trowel or spatula in lifts of 1” to 1 1/2” (25 to 38 mm) prior to the primer coat becoming tack-free. Allow each lift to set before applying subsequent lifts. **Pressure grouting: Vertical cracks:** Attach injection ports and seal the face of the crack with Dural Fast Set Gel or Dural 452 Gel. Allow the sealing gel to sufficiently harden before injecting. Pump DURAL FAST SET LV into the crack with two-component pressure injection equipment; starting at the bottom of the crack and working up. Work from port to port and cap off ports as you proceed up the crack to contain the DURAL FAST SET LV within the crack. DO NOT INJECT if water is leaking from the crack. Consult Euclid Chemical’s Technical Service Department regarding the use of the Dural Aqua-Dam products for leaking cracks. **Horizontal cracks:** Open cracks by mechanical means and ensure that the prepared crack is free of all debris and standing water. Pressure injection technique is the same as for vertical cracks. If gravity feeding, dispense DURAL FAST SET LV until cracks are completely filled. If working on an elevated slab, ensure the bottom of the slab is sealed prior to injecting or gravity feeding the crack so the epoxy doesn’t leak through.

CLEAN-UP

Clean tools and application equipment immediately after use with EUCO SOLVENT or acetone while still wet.

PRECAUTIONS/LIMITATIONS

- Store at temperatures between 50°F to 90°F (10°C to 32°C)
- Do not thin
- Protect from moisture
- Surface and ambient temperatures must be 35°F (2°C) and rising at time of use
- In all cases, consult the Safety Data Sheet before use

Rev. 11.14

WARRANTY: The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.